

Amendments to the Claims.

37. (Previously Added) A weatherseal for releasably contacting a panel, comprising:

- gws
cl
- (a) a substrate; and
 - (b) a contact layer on at least a portion of the substrate, the contact layer including a thermoset carrier and a multitude of UHMW polyethylene particles having a polar functional group, the UHMW polyethylene particles chemically bonded to the thermoset carrier to form surface projections.

38. (Previously Added) The weatherseal of Claim 37, wherein the thermoset carrier includes cross-linked urethane.

39. (Currently Amended) The weatherseal of Claim 37, wherein the substrate includes ~~one of an EPDM, a thermoplastic and a thermoplastic elastomer.~~

gws
cl
200

40. (Currently Amended) A weatherseal, comprising:

- (a) a substrate ~~including one of an EPDM, a thermoplastic and a thermoplastic elastomer;~~ and
- (b) a contact layer on the substrate, the contact layer including projection forming surface treated UHMW polyolefin particles in a cross linked urethane based carrier, ~~the surface treated UHMW polyolefin particles.~~

41. (Previously Added) The weatherseal of Claim 40, wherein the UHMW polyolefin particles are cross-linked.

gws
cl

42. (Previously Added) A weatherseal contact layer having a multitude of projections, comprising a multitude of coefficient of friction reducing projection forming surface treated thermoplastic particles bonded to a cured thermoset carrier.

43. (Previously Added) The contact layer of Claim 42, wherein the thermoplastic particles are an ultra high molecular weight olefin.

44. (Previously Added) The contact layer of Claim 42, wherein the thermoplastic particles are surface treated UHMW polyethylene.

45. (Previously Added) The contact layer of Claim 42, wherein the thermoset carrier includes urethane.

46. (Previously Added) The contact layer of Claim 42, wherein the thermoplastic particles have a melting temperature greater than a curing temperature of the thermoset carrier.

47. (Previously Added) A weatherseal, comprising:

(a) a substrate; and

(b) a contact layer on a portion of the substrate, the contact layer having a multitude of surface treated olefinic particles in a cured thermoset urethane based carrier, the surface treated olefinic particles sized to create friction reducing surface projections in the contact layer.

48. (Currently Amended) The weatherseal of Claim 47, wherein the substrate includes ~~one of an EPDM, a thermoplastic and a thermoplastic elastomer.~~

49. (Previously Added) The weatherseal of Claim 47, wherein the surface treated olefinic particles are UHMW polyethylene.

50. (Previously Added) The weatherseal of Claim 47, wherein the surface treated olefinic particles are chemically bonded to the cured thermoset urethane based carrier.

51. (Previously Added) The weatherseal of Claim 47, wherein the surface treated olefinic particles are cross-linked.

52. (Currently Amended) The weatherseal of Claim 47, wherein the surface treated olefinic particles are sufficiently bonded to the cured thermoset urethane based carrier to ~~substantially~~ preclude non-destructive separation during use of the weatherseal.

53. (Previously Added) The weatherseal of Claim 47, wherein the surface treated olefinic particles are encapsulated within the cured thermoset urethane based carrier.

54. (Previously Added) The weatherseal of Claim 47, wherein the surface treated olefinic particles have a polar functional group.

55. (Previously Added) The weatherseal of Claim 47, wherein a melting temperature of the surface treated olefinic particles is greater than a curing temperature of the urethane based carrier.

56. (Previously Added) A method of forming a weatherseal, comprising:

56. (Previously Added) A method of forming a weatherseal, comprising:
- (a) forming a substrate;
 - (b) mixing a multitude of surface treated olefinic particles and a curable thermoset urethane based carrier;
 - (c) disposing the mixed surface treated olefinic particles and the curable thermoset urethane based carrier on a portion of the substrate; and
 - (d) curing the curable thermoset urethane based carrier as it is disposed on the substrate to retain discrete surface treated olefinic particles and form surface projections.

57. (Previously Added) A weatherseal, comprising:

- (a) a substrate; and
- (b) a contact layer on a portion of the substrate, the contact layer having a multitude of surface treated olefinic particles in a cured thermoset urethane based carrier, the surface treated olefinic particles having a melting temperature greater than a curing temperature of the urethane based carrier.

58. (Currently Amended) The weatherseal of Claim 57, wherein the substrate includes ~~one of an EPDM, a thermoplastic and a thermoplastic elastomer.~~

59. (Previously Added) The weatherseal of Claim 57, wherein the surface treated olefinic particles are UHMW polyethylene.

60. (Previously Added) The weatherseal of Claim 57, wherein the surface treated olefinic particles are chemically bonded to the cured thermoset urethane based carrier.

61. (Previously Added) The weatherseal of Claim 57, wherein the surface treated olefinic particles are cross-linked.

62. (Previously Added) The weatherseal of Claim 57, wherein the surface treated olefinic particles are sufficiently bonded to the cured thermoset urethane based carrier to substantially preclude separation.

63. (Previously Added) The weatherseal of Claim 57, wherein a plurality of the surface treated olefinic particles are encapsulated within the cured thermoset urethane based carrier.

64. (Previously Added) The weatherseal of Claim 57, wherein the surface treated olefinic particles have a polar functional group.

65. (Previously Added) A weatherseal, comprising:

(a) a substrate; and

(b) a contact layer on a portion of the substrate, the contact layer having a multitude of surface treated olefinic particles in a cured thermoset carrier, the surface treated olefinic particles having a melting temperature greater than a curing temperature of the thermoset carrier.

66. (Currently Amended) The weatherseal of Claim 65, wherein the substrate includes ~~one of an EPDM, a thermoplastic and a thermoplastic elastomer.~~

67. (Previously Added) The weatherseal of Claim 65, wherein the surface treated olefinic particles are UHMW polyethylene.

68. (Previously Amended) The weatherseal of Claim 65, wherein the surface treated olefinic particles are chemically bonded to the cured thermoset carrier.

69. (Previously Amended) The weatherseal of Claim 65, wherein the surface treated olefinic particles are cross-linked.

70. (Previously Amended) The weatherseal of Claim 65, wherein the surface treated olefinic particles are sufficiently bonded to the cured thermoset carrier to substantially preclude separation.

71. (Previously Amended) The weatherseal of Claim 65, wherein a plurality of the surface treated olefinic particles are encapsulated within the cured thermoset carrier.

443
C1
72. (Previously Amended) The weatherseal of Claim 65, wherein the surface treated olefinic particles have a polar functional group.

73. (New) The weatherseal of Claim 37, wherein the substrate includes a thermoplastic.

74. (New) The weatherseal of Claim 37, wherein the substrate includes a thermoplastic elastomer.

75. (New) The weatherseal of Claim 40, wherein the substrate includes an EPDM.

76. (New) The weatherseal of Claim 40, wherein the substrate includes a thermoplastic.

77. (New) The weatherseal of Claim 40, wherein the substrate includes a thermoplastic elastomer.

78. (New) The weatherseal of Claim 47, wherein the substrate includes a thermoplastic.

79. (New) The weatherseal of Claim 47, wherein the substrate includes a thermoplastic elastomer.

80. (New) The weatherseal of Claim 57, wherein the substrate includes a thermoplastic.

81. (New) The weatherseal of Claim 57, wherein the substrate includes a thermoplastic elastomer.

82. (New) The weatherseal of Claim 65, wherein the substrate includes a thermoplastic.

83. (New) The weatherseal of Claim 65, wherein the substrate includes a thermoplastic elastomer.